



Brussels, 31 January 2017

TM 1020:2017

Determination of the long term Thermal Conductivity of an OCF¹ Canister Foam

1. Scope

This method describes how to determine the long term thermal conductivity of a cured OCF foam, dispensed from a pressurised can, with a sample subjected to accelerated ageing procedure.

2. Short description of procedure

The test specimen is prepared by foaming into a mould made of two wooden plates and spacers. After curing, the two sides of the mould are open and the foam sample removed. The sample is then cut into the desired dimensions, depending on the measuring device to be used of e.g. 300 x 300 mm or 200 x 200 mm. The test is carried out on the basis of EN 12667 with a mean temperature of 10°C.

3. Background and purpose

One of the most important characteristics of polyurethane foam is its very good thermal insulation. When OCF foam is used as sealing and insulation of windows and external doors; low insulation value is of great importance.

4. Equipment

- 2 wooden plates (chipboard), e.g. size: 400 x 400 x 10 mm
- 2 spacers (chipboard), e.g. size: 400 x 30 x 10 mm
- PE foil
- 4 screw clamps
- Water
- Sharp cutter
- Balance with accuracy of 0,1 g.
- Testing machine (e. g. Lasercomp or Netzsch)

5. Procedure

It is necessary to complete at least three measurements to obtain a statistically relevant mean value.

¹ **OCF**: Generic term for moisture-curing One-Component Foams dispensed from pressurised containers ("aerosol cans") as well as self-curing two-component foams dispensed from pressurised containers ("1.5 component foams").

5.1 Preparation

- a) Acclimatise the test canister, wooden plates and spacers for 24 h at 23°C/50% R.H.
- b) Prepare the mould by placing the 30 mm thick spacers between the wooden plates (surrounded with PE foil) and tightening them with the clamps.
- c) Shake the canister vigorously 20 times.
- d) Spray the OFC foam in several layers between the plates. Moisten before applying each layer.
- e) After 24 h. the foam sample can be removed and cut to the desired dimensions.
- f) Store the foam samples for 21 days in oven at 70°C for ageing.
- g) Prepare the measuring device. Set the mean temperature difference between the hot and cold plate on 10°C, with the temperature difference between the two plates for example 5°C and 15°C.
- h) Carry out the test on the basis of EN 12667.



5.2 Evaluation

Report:

- Name of test specimen.
- The length, width, thickness and density of the test specimen.
- Mean temperature of the hot plate in °C.
- Mean temperature of the cold plate in °C.
- Mean temperature difference between hot and cold plate in °C.
- Declared thermal conductivity in W/mK.

6. Revision

Version	Date	Remarks
2	8 November 2016	Revised and checked by FEICA
3	31 January 2017	Revised and checked by FEICA

7. Sample Preparation

Before spraying the foam



Before spraying the foam (side view)



Spraying foam



Spraying water after each layer of foam



Leave to cure for 24 hours



Cut the expand foam to the desired dimensions





Final panel that is to be tested





8. Contact

FEICA – Association of the European Adhesive & Sealant Industry
Avenue Edmond van Nieuwenhuysse, 4
B- 1160 Brussels, Belgium
Tel: +32 (0)2 676 73 20 | Fax: +32 (0)2 676 73 99
info@feica.eu | www.feica.eu

FEICA, the Association of the European Adhesive & Sealant Industry is a multinational association representing the European Adhesive and Sealant Industry. With the support of its national associations and several direct and affiliated members, FEICA coordinates, represents and advocates the common interests of our industry throughout Europe. In this regard FEICA aims at establishing a constructive dialogue with legislators in order to act as a reliable partner to resolve issues affecting the European Adhesive and Sealant Industry.

Publication ref.: TM-1020:2017

Copyright ©FEICA, 2017

Reproduction is authorised provided the source is fully acknowledged in the form: `Source: FEICA TM-1020:2017, <http://www.feica.eu>`.

This document has been designed using the best knowledge currently available, and is to be relied upon at the user's own risk. The information is provided in good faith and no representations or warranties are made with regards to the accuracy or completeness, and no liability will be accepted for damages of any nature whatsoever resulting from the use or reliance on this paper. This document does not necessarily represent the views of all member companies of FEICA.